



ALFLEX PLATE 0.125" (3mm) TECHNICAL DATA SHEET

COMPOSITION

| | |
|----------------------|----------|
| Aluminum Plate Alloy | 3003-H14 |
|----------------------|----------|

STANDARD SIZES

| PROPERTY | VALUES | UNITS |
|--|---------------|-------|
| Standard Thickness (nominal) | 0.125 | in |
| | 3.0 | mm |
| Other Available Thicknesses (nominal) | 0.080 | in |
| | 2.0 | mm |
| Standard Width | 49.2 62.0 | in |
| | 1,250 1,578 | mm |
| Custom Width Range | 31.5 - 62.0 | in |
| | 800 - 1600 | mm |
| Standard Length (max) | 165 | in |
| | 4191 | mm |

PRODUCTION TOLERANCES

| PROPERTY | VALUES | UNITS |
|-----------|-----------|-------|
| Width | +/- 0.080 | in |
| | 2.0 | mm |
| Length | +/- 0.157 | in |
| | 4.0 | mm |
| Thickness | +/- 0.004 | in |
| | 0.10 | mm |

ASTM B209 COMPLIANCE: 3003-H14 ALUMINUM

CHEMICAL COMPOSITION

| ELEMENT | STANDARD | RESULTS |
|----------------|---------------|---------|
| Aluminum | Remainder | 97.75% |
| Copper | 0.05% - 0.2% | 0.17% |
| Iron | 0.0% to 0.7% | 0.56% |
| Manganese | 1.0% - 1.5% | 1.19% |
| Silicon | 0.0% to 0.6% | 0.18% |
| Zinc | 0.0% to 0.1% | 0.00% |
| Other Elements | 0.0% to 0.15% | 0.15% |

MECHANICAL PROPERTY LIMITS

| PROPERTY | STANDARD | RESULTS |
|----------------|-------------------------|----------|
| Tensile (ksi) | 20 ksi min - 26 ksi max | 21.4 ksi |
| Yield Strength | 17 ksi min | 18.5 ksi |
| Elongation | 2% Min | 25% |

FINISH WARRANTY

See warranty tables and sample warranties for conditions and exclusions

| | |
|-------------------------|----------|
| PVDF Coil Coated Finish | 20 Years |
|-------------------------|----------|

Alfrex, LLC endeavors to provide accurate and current technical information but cannot warrant or make any representations as to the accuracy or completeness of the information contained herein. All data is intended for informational purposes only and subject to change without notice. Please consult a licensed structural engineer for evaluations of structural soundness, specification, or final design.

TECHNICAL PROPERTIES

| PROPERTY | | VALUES | UNITS |
|----------------------------|---------|-------------------------|--------------------------|
| Panel Weight | | 1.66 | lb/ft ² |
| | | 8.10 | kg/m ² |
| Specific Gravity (Product) | | 2.72 | g/cc |
| Coefficient of Expansion | | 12.9 | in/in/°F (@ 68-212°F) |
| Modulus of Elasticity | ASTM E8 | 10 X 10 ⁶ | Psi |
| | | 69X 10 ³ | Mpa |
| Moment of Inertia | | 1.37 X 10 ⁻⁴ | in ⁴ /in |
| | | 5.7 X 10 ⁻³ | cm ⁴ /m |
| Section Modulus | | 2.32X 10 ⁻³ | in ³ /in |
| | | 38.0 X 10 ⁻³ | cm ³ /m |
| Tensile Strength | ASTM E8 | 20.3 X 10 ³ | Psi |
| | | 140 | Mpa |
| Yield Strength | ASTM E8 | 17.4X 10 ³ | Psi |
| | | 120 | Mpa |
| Elongation | ASTM E8 | 5 | % |
| Thermal Conductivity | C518 | 193 | W/(m•K) |

ARCHITECTURAL COATING PERFORMANCE

AAMA 2605-13 STANDARD COMPLIANCE

70% Kynar 500 / Hylar 5000 PVDF Resin Coatings

| PROPERTY | TEST STANDARD | REQUIREMENT | RESULTS |
|--|---------------|--|---|
| Dry Film Thickness | ASTM D7091 | ≥ 23 microns | Pass - 32 microns |
| Color Uniformity | ASTM D2244 | Max. 2 Delta E | Pass - < 2 units |
| Color Retention - Fade | ASTM D2244 | Delta E ≤ 5 units | Pass - < 5 units |
| Chalk Rating | ASTM D4214 | ≤ 8 units | Pass - < 8 units |
| Specular Gloss | ASTM D523 | ± 5 units | Pass |
| Dry Film Hardness | ASTM D3363 | F - 2H | Pass - 3H |
| Dry Adhesion | ASTM D3359 | No coating removal | Pass - no removal |
| Abrasion Resistance | ASTM D968 | Abrasion Coefficient Value ≥ 40 | Pass - 51 |
| Reverse Impact | ASTM D2794 | No coating removal | Pass - no removal |
| Muriatic Acid Resistance (10% HCl, 15 mins) | ASTM D1308 | No blistering or visual change | Pass - no blistering or visual changes |
| Nitric Acid Resistance (HNO ₃ , 30 mins) | ASTM D1308 | ≤ 5 Delta E | Pass - 0.2 |
| Alkali Mortar Resistance (10%, 25% NaOH, 60 mins) | ASTM D1308 | No removal. No loss of adhesion or visual change | Pass - no adhesion loss |
| Flexibility | ASTM D4145 | 2T - no pick off | Pass - no pick off |
| Humidity Resistance | ASTM D714 | 4000 hour exposure | Pass - No #8 blisters |
| | ASTM D2247 | Less than "few" blisters Size No. 8 | |
| Cyclic Corrosion | ASTM B117 | 2000 hour exposure. | Pass - 10 rating |
| | AAMA 2605-13 | Min rating of 7 scribe or cut edge Min. blister rating of 8 | |

FIRE PERFORMANCE FOR NON-COMBUSTIBILITY

| STANDARD | STANDARD TEST METHOD | RESULTS |
|---------------|--|------------------------|
| ASTM E136 | Behavior of Materials in a Vertical Tube Furnace at 750°C. | PASS Meets Standard |
| CAN/ULC S114* | Determination of Non-Combustibility of Building Materials | PASS Meets Standard |
| CAN/ULC S135* | Determination of Combustibility Parameters of Building Materials Using an Oxygen Consumption Calorimeter | PASS Meets Standard |

* Test Conducted on 3mm Plate